



Pierre Frey sas 47 rue des Petits Champs 75001 PARIS France

Your notice of 01-06-2021

Your reference

Date 28-06-2021

Analysis Report 21.03618.35

Required tests:

EN 13773 (2003)

Sample id Information given by the client Date of receipt
T2113530 F3587 MONT FORAKER 16-06-2021

Gina Créelle Order responsible

réelle

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel. The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.







Reference: T2113530 - F3587 MONT FORAKER

<u>Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the ignitability of vertically oriented specimens.</u>

Date of ending the test 22-06-2021

Standard used EN 1101 (1995) + A1 (2005)

Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

Ignition Bottom edge

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length

Flame application	Cases of	Cases of		
time (s)	ignition	non-ignition		
1	0	1		
2	0	1		
3	0	1		
4	0	1		
5	0	1		
10	0	1		
15	0	1		
20	0	5		

The mean of the recorded times at which ignition was observed is calculated No ignition within $20\ \mathrm{s}$





Width

Flame application	Cases of	Cases of		
time (s)	ignition	non-ignition		
1	0	1		
2	0	1		
3	0	1		
4	0	1		
5	0	1		
10	0	1		
15	0	1		
20	0	5		

The mean of the recorded times at which ignition was observed is calculated No ignition within $20\ \mathrm{s}$



Reference: T2113530 - F3587 MONT FORAKER

<u>Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.</u>

Date of ending the test 25-06-2021

Standard used EN 13772 (2011) Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length

	Face A	Face B	Face B	Face B
Severance1st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	120	125	135	145
Flaming debris	no	no	no	no

Width

	Face A	Face B	Face A	Face A
Severance1st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	130	130	135	130
Flaming debris	no	no	no	no

Classification in accordance with EN Class 1 13773